



# CAB-O-SIL

**CAUTION:** Avoid breathing dust. Wash thoroughly after handling.

**PROTECTION:** Respiratory: Use NIOSH approved dust respirator.

Eyes: Safety glasses/goggles.

Contains: Amorphous Fumed Silica.

**KEEP OUT OF REACH OF CHILDREN.**

**the fantastic  
plastic place**

For more information,  
ask for, or download  
TAP Product Bulletin 14  
from our website  
[tapplastics.com](http://tapplastics.com)

MSDS for  
TAP Cab-O-Sil  
available at  
[tapplastics.com](http://tapplastics.com)

**Fine • White • Odorless • Powder**

- **thixotropic/controls sagging**
- **allows ease in working with vertical/overhead surfaces**
- **increases hardness of resin**

**NET WT. 1.5 oz.**

**TAP Plastics Inc • San Leandro CA 94577**

**INSTRUCTIONS:** Mix Resin and Hardener thoroughly. Gradually stir in Cabosil to desired thickness. Curing process begins when Hardener is added, watch working-time.

**Creamy Texture:** 3 oz Cabosil per gallon of Resin-Hardener mix.

**Paste Texture:** 3 oz Cabosil per quart of Resin-Hardener mix.

Combine Cabosil with milled fibers for a non-sagging structural adhesive or with microballons to impart easier sanding.

**Visit us on the web: [www.tapplastics.com](http://www.tapplastics.com)**