

**TAP Plastics  
Platinum  
Silicone • Side B**

**PROPERTIES**

Viscosity	900-1100 cP
Mixing time	~1 minute @ 73°F
Working time	~15-18 minutes @ 73°F
Cure time	~ 2 hours @ 73°F
Shore A	8 +- 1 ShA @ 24 hours
Tensile Strength	218 psi
Elongation at Break	280%
Max Service Temp	~500°F
Exotherm	Minimal

**WARRANTY**

TAP products are manufactured to quality specifications, however they should be tested to determine their suitability for your application. Since we have no control over working conditions or methods, our liability does not exceed the value or replacement of this product. TAP Resin products are guaranteed for six months from date of purchase or nine months from code date on container.

# PLATINUM



# SILICONE SIDE B CATALYST

**One to One**

- Super Soft Formula
- Platinum Cure
- Flexible for deep undercuts
- No Vacuum required

**Net. 32 fl oz**  
**Use with Side A (Base)**

*Quality Products Since 1952*

**TAP Plastics Inc.**

San Leandro, CA 94577

the fantastic plastic place • [tapplastics.com](http://tapplastics.com)

**TAP Plastics  
Platinum  
Silicone • Side B**

**READ SIDE A  
FOR INSTRUCTIONS**

Materials to avoid when working with platinum cure silicone (they can prevent the silicone from curing):

- Tin containing compounds such as tin cure silicone
- Sulfur or nitrogen containing compounds such as latex, wood, PVC, Neoprene Rubber, epoxy.
- The following common items:
  - Scotch tape
  - Vinyl electrical tape,
  - Acid or Rosin core solder flux
  - Some masking tapes.
  - Some pigments and dyes.

**CAUTION**

For eye contact flush with plenty of water. If irritation persists, seek medical advice. Ingestion: seek medical attention.

**KEEP OUT OF REACH OF CHILDREN.**

Rev. 4/22/11

CODE DATE: 22348