

SILICONE RTV



THINNER FOOD GRADE

Use with
TAP Silicone RTV System

- Primarily used as a diluent or thinner to reduce the viscosity of TAP Silicone RTV rubbers.
- Ideal to make “skin coat” on intricate parts.

Net 8 fl oz

TAP Plastics, Inc.

San Leandro CA 94577 • www.tapplastics.com

Mix Ratios (by weight):

TAP SILICONE RTV Side A	100 parts
TAP SILICONE RTV CATALYST Side B	10 parts
TAP SILICONE RTV THINNER	1 parts – 10 parts

CAUTIONS:

In case of eye contact, flush at least 15 minutes with water. Obtain medical attention if irritation persists. Wash after skin contact. Follow all instructions for safe use. **KEEP AWAY FROM CHILDREN.**

MIXING GUIDELINES:

- The addition of 5-10 parts by weight added to 100 parts of the mixed TAP SILICONE RTV rubber is sufficient to adequately reduce the viscosity for most applications.
- The addition of 10 parts of the TAP SILICONE THINNER is the MAXIMUM level recommended.
- The addition of greater amounts will significantly affect the physical properties of the cured rubber and may also cause the fluid to bleed out of the cured rubber.
- FDA approved for food contact.
- Thinner may increase the working time, decrease mold hardness and tear strength.

Date Code: 22185

Rev. 11/3/11