

- **Slow Cure**
- **100% Solids**
- **No Solvents**
- **Low Viscosity**
- **Excellent Chemical Resistance**

143 HARDENER is a SLOW curing hardener for use with 314 Resin.

143 Hardener has the ability to cure at warm or cold temperatures. Allows application of second coat in approximately 5 hours.


Date Code: 22340

Rev. 3/25/11

#### WARRANTY

TAP products are manufactured to quality specifications, however they should be tested to determine their suitability for your application. Since we have no control over working conditions or methods, our liability does not exceed the value or replacement of this product. TAP Resin products are guaranteed for six months from date of purchase or nine months from code date on container.

# MARINE GRADE



**TAP**

# EPOXY SYSTEM

## PREMIUM

# SIDE B

## 143 HARDENER SLOW

See CAUTIONS on Label.

## Net 1 Gallon Use with TAP 314 Resin

Quality Products Since 1952

**TAP Plastics Inc.**  
San Leandro, CA 94577

### DIRECTIONS FOR USE

Mix 2-parts of Side A, 314 Resin, with 1-part of Side B, Hardener (by volume), into a clean container. Stir for 1 to 2 minutes, using care to scrape sides and bottom of container to mix thoroughly. Never vary the Resin to Hardener ratio. Mix only the amount that can be used within 25 minutes. **To extend pot-life, transfer the mixed Resin to a shallow container such as a paint tray.** 143 Hardener will cure at temperatures as low as 40°F. To ensure proper cure at lower temperatures, be sure that the Resin and Hardener are at room temperature (72°F) before mixing. A low temperature will increase viscosity and cure time.

See TAP Product Bulletins 12 (Premium Marine Grade Epoxy) and 14 (Use Filler to Transform Resins) for more information.

### CAUTIONS

Avoid breathing vapors. Use in well ventilated area. May cause allergic skin reaction. Wear protective clothing.

### KEEP AWAY FROM CHILDREN • FIRST AID

**Eyes:** Hold eyelids apart and flush eyes with water for at least 15 minutes. Call a physician.

**Ingestion:** May be harmful. Do not induce vomiting unless directed by medical personnel. Seek medical attention.

**Inhalation:** Remove patient to fresh air. Call a physician.

**Skin:** Remove excess product. Wash thoroughly with soap and water. If irritation persists, seek medical attention.

MSDS for TAP Marine Grade Epoxy System  
available at [tapplastics.com](http://tapplastics.com)