

Surfacing Veil

Technical Data Sheet*



TAP Plastics

Fiber	C-Glass
Binder System	soluble in styrene
Structure of nonwoven	random
Weight DIN 53854	0.77 oz./yd. ² 26 gm/m ²
Thickness DIN 53855/1	0.010 (in.) 0.26 (mm)
Max. tensile strength DIN 52857 m.d.	5.6 (lbs./2") 25 (N/50 mm)
Max. tensile strength DIN 52857 a.m.d.	3.4 (lbs./2") 15 (N/50 mm)
Elongation at max DIN 53857 m.d. tensile strength	1%
Elongation at max DIN 53857 a.m.d. tensile strength	1%
Resin absorbtion (company specification)	9.4 oz./yd. ² 320 g/m ²
Width available Standard	35.5 (in.) 900 (mm)

*Average vaules which are subject to normal production deviations.