

## Fiberglass Reinforced Plastic Pultruded Rod and Bar

## **Typical Properties**

Ultimate Tensile Strength

Ultimate Flexural Strength

120,000 psi min

120,000 psi min

120,000 psi min

70,000 psi min

Modulus of Elasticity

6.0 x 10<sup>6</sup> psi

Izod Impact Ft.-lb. per inch

40 min

Dielectric Strength 360 volts/mil min

Dielectric Constant at 60 Hz 6.6

ARC Resistance (ASTM D495) 186 seconds

ARC Resistance 100 KV/Ft. - No damage

Specific Gravity 2.0 Glass Content 76%

Density .073 lbs/in<sup>3</sup>

Water Absorption 0.5%

Weight increase after 24 hours immersion

Thermal Coefficient of Expansion 3 x 10<sup>-6</sup>

inches/inch/°F

Thermal Conductivity 2.1

BTU per sq ft/hr/°F/in

Specific Heat 0.24

BTU/lb/°F

Visit our website: tapplastics.com

Please note above data is representative of a specific formula and is not typical of all custom formulated parts. The information given is based on data received of others and is presented with every belief in its accuracy. Due to variable conditions, TAP Plastics makes no warranty, including the implied warranty of merchantability and fitness for particular purpose, nor any recommendations made to infringe on patents.