



Type • This resin is a specially promoted, medium reactivity, low viscosity, orthophthalic, U.V. stabilized resin promoted for room temperature cure using Methyl Ethyl Ketone Peroxide.

Recommended Use • Surfboard Resin is specifically formulated to be used for the laminating step in hand lay-up products such as surfboard and sailboards. This resin provides superior resistance to cracking and good handling properties.

Typical Inspection of Liquid Resin

Color	Clear Blue
Monomer Content, %	37 - 41
Viscosity, Brookfield Model, LVF #3 Spindle @ 60 rpms, cps	300 - 455
Specific Gravity	1.11 - 1.13
Storage Stability @ 25°C, months	6

Typical Reactivity - 100 grams (3.53 oz) casting @ 25°C

Catalyst	1.25% MEKP - 9%
Gel Time, minutes	7 - 10

Typical Physical Properties

Clear Casting with 1.25% MEKP, overnight room temperature cure, 2 hr. post cure

Barcol Hardness	ASTM D-2583-75	40 - 42
Heat Deflection Temp. °C (°F)	ASTM D-648-72	60 (140)
Tensile Strength, psi	ASTM D-638-80	9,650
Flexural Strength	ASTM D-790-80	15,400
Flexural Modulus, psi x 105	ASTM D-790-80	5.96
Water Absorption, % 2 hr. boiling	ASTM D-570-77	1.16
Water Absorption, % 24 hr. rm. tp.	ASTM D-570-77	0.09

Disclaimer and Limitation of Warranty

The information herein is to assist customers in determining whether this product is suitable for their applications. Our products are intended for sale to commercial and industrial customers. We request that customers inspect and test our products before use and satisfy themselves as to contents and suitability. We warrant that our products will meet our written specifications. Nothing herein shall constitute any other warranty express or implied, including any warranty of merchantability or fitness, nor is protection from any law or patent to be inferred. All patent rights are reserved. The exclusive remedy for all proven claims is replacement of our materials and in no event shall we be liable for special, incidental or consequential damages.