



MEKP Catalyst Ratios

Peroxide Concentration	1 qt Resin	1 gal Resin	5 gal Resin
1.0%	10 cc 0.4 oz	38 cc 1.5 oz	188 cc 7.4 oz
1.25%	12 cc 0.5 oz	47 cc 1.8 oz	235 cc 9.2 oz
1.5%	14 cc 0.6 oz	56 cc 2.2 oz	282 cc 11 oz
2.0%	19 cc 0.7 oz	75 cc 2.9 oz	376 cc 14.7 oz

cc=cubic centimeter

oz=ounces (weight not volume)

These calculations are based on 9.2 pounds per gallon resin and 1.11 grams per cubic centimeter MEKP