



# Skyrol® Polyester Film

## SH82

## Product Information

### ● Product Description

Skyrol® SH82 is an optically clear, glossy, two side chemically treated film. It provides an enhanced adhesion to various inks and adhesives.

SH82 film is available in a range of thickness from 200ga to 750ga, and is used for high quality printing and solvent coating applications.

SH82 film is FDA approved for direct food contact in compliance with FDA 21 CFR 177.1630 (f).

### ● Typical Properties

Property	Unit	Value					Test Method
<b>General</b>							
Nominal Thickness	Gauge ( μm )	500 (125)	600 (150)	650 (165)	700 (175)	750 (188)	SKC Method
<b>Mechanical</b>							
Tensile Strength	Kpsi MD	25.0	24.0	23.0	22.0	21.0	ASTM D882
	TD	29.0	28.0	27.0	26.0	25.5	
Elongation At Break	% MD	195	215	235	250	255	ASTM D882
	TD	140	145	150	150	150	
<b>Surface</b>							
Coefficient of Friction	μk (Kinetic)	0.39	0.39	0.39	0.39	0.39	ASTM D1894
	μs (Static)	0.43	0.43	0.43	0.43	0.43	
Surface Tension	Dyne Chemical	36	36	36	36	36	ASTM D 2578
<b>Optical</b>							
Haze	%	1.60	1.70	1.80	2.10	2.70	ASTM D1003
Light Transmission	%	90.0	89.9	89.5	89.5	88.9	ASTM D1003
Gloss	%	185	180	180	180	175	ASTM D523
<b>Thermal</b>							
Heat Shrinkage	% MD	1.0	0.9	0.9	0.9	0.9	SKC Method ( 150°C×30 min )
	TD	0.6	0.5	0.5	0.5	0.5	

\* Unit Correlation : N/mm<sup>2</sup> = Kg/mm<sup>2</sup> x 9.8

Kg/mm<sup>2</sup> = Kpi / 1.4223

SKCA-A-13

This Information is the best currently available on the subject. The results should, however, only be regarded as a general guide to material properties and not as a guarantee.

Some of the properties can be changed as a result of supplier's efforts to improve the quality or production efficiency of the subject.

Note: Please read the Material Safety Data Sheet(MSDS) carefully prior to use.



## SH82 (200ga)

## Product Information

### ● Product Description

Skyrol® SH82 is an optically clear, glossy, two side chemically treated film. It provides an enhanced adhesion to various inks and adhesives. SH82 film is available in a range of thickness from 200ga to 750ga, and is used for high quality printing and solvent coating applications.

SH82 film is FDA approved for direct food contact in compliance with FDA 21 CFR 177.1630 (f).

### ● Typical Properties

Property	Unit	Value	Test Method
<b>General</b>			
Nominal Thickness	(Gauge) µm	<b>200</b> ( 50 )	SKC Method
<b>Mechanical</b>			
Tensile Strength	psi MD (Kg/mm <sup>2</sup> ) TD	28,500 (20) 33,000 (23)	ASTM D 882
Elongation At Break	% MD TD	165 125	ASTM D 882
<b>Surface</b>			
Coefficient of Friction	µk (Kinetic) µs (Static)	0.38 0.43	ASTM D1894
Surface Tension	Dyne Chemical	36	ASTM D 2578
<b>Optical</b>			
Haze	%	0.90	ASTM D 1003
Light Transmission	%	90.3	ASTM D 1003
Gloss	%	190	ASTM D 523
<b>Thermal</b>			
Heat Shrinkage	% MD TD	1.0 0.6	SKC Method ( 150°C×30 min )

Unit Correlation : N/mm<sup>2</sup> = Kg/mm<sup>2</sup> × 9.8  
Kg/mm<sup>2</sup> = psi / 1422.3

SKCA-A-13

This Information is the best currently available on the subject. The results should, however, only be regarded as a general guide to material properties and not as a guarantee. Some of the properties can be changed as a result of supplier's efforts to improve the quality or production efficiency of the subject.  
Note: Please read the Material Safety Data Sheet(MSDS) carefully prior to use.



## SH82 (265ga)

## Product Information

### ● Product Description

Skyrol® SH82 is an optically clear, glossy, two side chemically treated film. It provides an enhanced adhesion to various inks and adhesives. SH82 film is available in a range of thickness from 200ga to 750ga, and is used for high quality printing and solvent coating applications.

SH82 film is FDA approved for direct food contact in compliance with FDA 21 CFR 177.1630 (f).

### ● Typical Properties

Property	Unit	Value	Test Method
<b>General</b>			
Nominal Thickness	(Gauge) µm	<b>265</b> ( 67 )	SKC Method
<b>Mechanical</b>			
Tensile Strength	psi MD (Kg/mm <sup>2</sup> ) TD	27,000 (19) 33,000 (23)	ASTM D 882
Elongation At Break	% MD TD	180 130	ASTM D 882
<b>Surface</b>			
Coefficient of Friction	µk (Kinetic) µs (Static)	0.38 0.43	ASTM D1894
Surface Tension	Dyne Chemical	36	ASTM D 2578
<b>Optical</b>			
Haze	%	1.00	ASTM D 1003
Light Transmission	%	90.2	ASTM D 1003
Gloss	%	190	ASTM D 523
<b>Thermal</b>			
Heat Shrinkage	% MD TD	1.0 0.6	SKC Method ( 150°C×30 min )

Unit Correlation : N/mm<sup>2</sup> = Kg/mm<sup>2</sup> × 9.8  
Kg/mm<sup>2</sup> = psi / 1422.3

SKCA-A-13

This Information is the best currently available on the subject. The results should, however, only be regarded as a general guide to material properties and not as a guarantee. Some of the properties can be changed as a result of supplier's efforts to improve the quality or production efficiency of the subject.  
Note: Please read the Material Safety Data Sheet(MSDS) carefully prior to use.



## SH82 (300ga)

## Product Information

### ● Product Description

Skyrol® SH82 is an optically clear, glossy, two side chemically treated film. It provides an enhanced adhesion to various inks and adhesives. SH82 film is available in a range of thickness from 200ga to 750ga, and is used for high quality printing and solvent coating applications.

SH82 film is FDA approved for direct food contact in compliance with FDA 21 CFR 177.1630 (f).

### ● Typical Properties

Property	Unit	Value	Test Method
<b>General</b>			
Nominal Thickness	(Gauge) µm	<b>300</b> ( 75 )	SKC Method
<b>Mechanical</b>			
Tensile Strength	psi MD (Kg/mm <sup>2</sup> ) TD	26,500 (19) 32,000 (22)	ASTM D 882
Elongation At Break	% MD TD	180 130	ASTM D 882
<b>Surface</b>			
Coefficient of Friction	µk (Kinetic) µs (Static)	0.39 0.43	ASTM D1894
Surface Tension	Dyne Chemical	36	ASTM D 2578
<b>Optical</b>			
Haze	%	1.10	ASTM D 1003
Light Transmission	%	90.2	ASTM D 1003
Gloss	%	190	ASTM D 523
<b>Thermal</b>			
Heat Shrinkage	% MD TD	1.0 0.6	SKC Method ( 150°C×30 min )

Unit Correlation : N/mm<sup>2</sup> = Kg/mm<sup>2</sup> × 9.8  
Kg/mm<sup>2</sup> = psi / 1422.3

SKCA-A-13

This Information is the best currently available on the subject. The results should, however, only be regarded as a general guide to material properties and not as a guarantee. Some of the properties can be changed as a result of supplier's efforts to improve the quality or production efficiency of the subject.  
Note: Please read the Material Safety Data Sheet(MSDS) carefully prior to use.



## SH82 (380ga)

## Product Information

### ● Product Description

Skyrol® SH82 is an optically clear, glossy, two side chemically treated film. It provides an enhanced adhesion to various inks and adhesives. SH82 film is available in a range of thickness from 200ga to 750ga, and is used for high quality printing and solvent coating applications.

SH82 film is FDA approved for direct food contact in compliance with FDA 21 CFR 177.1630 (f).

### ● Typical Properties

Property	Unit	Value	Test Method
<b>General</b>			
Nominal Thickness	(Gauge) µm	<b>380</b> ( 96.5 )	SKC Method
<b>Mechanical</b>			
Tensile Strength	psi MD (Kg/mm <sup>2</sup> ) TD	25,500 (18) 30,000 (21)	ASTM D 882
Elongation At Break	% MD TD	185 140	ASTM D 882
<b>Surface</b>			
Coefficient of Friction	µk (Kinetic) µs (Static)	0.39 0.43	ASTM D1894
Surface Tension	Dyne Chemical	36	ASTM D 2578
<b>Optical</b>			
Haze	%	1.30	ASTM D 1003
Light Transmission	%	90.1	ASTM D 1003
Gloss	%	190	ASTM D 523
<b>Thermal</b>			
Heat Shrinkage	% MD TD	1.0 0.6	SKC Method ( 150°C×30 min )

Unit Correlation : N/mm<sup>2</sup> = Kg/mm<sup>2</sup> × 9.8  
Kg/mm<sup>2</sup> = psi / 1422.3

SKCA-A-13

This Information is the best currently available on the subject. The results should, however, only be regarded as a general guide to material properties and not as a guarantee. Some of the properties can be changed as a result of supplier's efforts to improve the quality or production efficiency of the subject.

Note: Please read the Material Safety Data Sheet(MSDS) carefully prior to use.



## SH82 (400ga)

## Product Information

### ● Product Description

Skyrol® SH82 is an optically clear, glossy, two side chemically treated film. It provides an enhanced adhesion to various inks and adhesives. SH82 film is available in a range of thickness from 200ga to 750ga, and is used for high quality printing and solvent coating applications.

SH82 film is FDA approved for direct food contact in compliance with FDA 21 CFR 177.1630 (f).

### ● Typical Properties

Property	Unit	Value	Test Method
<b>General</b>			
Nominal Thickness	(Gauge) µm	<b>400</b> ( 100 )	SKC Method
<b>Mechanical</b>			
Tensile Strength	psi MD (Kg/mm <sup>2</sup> ) TD	25,500 (18) 30,000 (21)	ASTM D 882
Elongation At Break	% MD TD	185 140	ASTM D 882
<b>Surface</b>			
Coefficient of Friction	µk (Kinetic) µs (Static)	0.39 0.43	ASTM D1894
Surface Tension	Dyne Chemical	36	ASTM D 2578
<b>Optical</b>			
Haze	%	1.40	ASTM D 1003
Light Transmission	%	90.1	ASTM D 1003
Gloss	%	190	ASTM D 523
<b>Thermal</b>			
Heat Shrinkage	% MD TD	1.0 0.6	SKC Method ( 150°C×30 min )

Unit Correlation : N/mm<sup>2</sup> = Kg/mm<sup>2</sup> × 9.8  
Kg/mm<sup>2</sup> = psi / 1422.3

SKCA-A-13

This Information is the best currently available on the subject. The results should, however, only be regarded as a general guide to material properties and not as a guarantee. Some of the properties can be changed as a result of supplier's efforts to improve the quality or production efficiency of the subject.  
Note: Please read the Material Safety Data Sheet(MSDS) carefully prior to use.



## SH82 (460ga)

## Product Information

### ● Product Description

Skyrol® SH82 is an optically clear, glossy, two side chemically treated film. It provides an enhanced adhesion to various inks and adhesives. SH82 film is available in a range of thickness from 200ga to 750ga, and is used for high quality printing and solvent coating applications.

SH82 film is FDA approved for direct food contact in compliance with FDA 21 CFR 177.1630 (f).

### ● Typical Properties

Property	Unit	Value	Test Method
<b>General</b>			
Nominal Thickness	(Gauge) µm	<b>460</b> ( 116.8 )	SKC Method
<b>Mechanical</b>			
Tensile Strength	psi MD (Kg/mm <sup>2</sup> ) TD	25,000 (18) 29,000 (20)	ASTM D 882
Elongation At Break	% MD TD	190 140	ASTM D 882
<b>Surface</b>			
Coefficient of Friction	µk (Kinetic) µs (Static)	0.39 0.43	ASTM D1894
Surface Tension	Dyne Chemical	36	ASTM D 2578
<b>Optical</b>			
Haze	%	1.50	ASTM D 1003
Light Transmission	%	90.0	ASTM D 1003
Gloss	%	187	ASTM D 523
<b>Thermal</b>			
Heat Shrinkage	% MD TD	1.0 0.6	SKC Method ( 150°C×30 min )

Unit Correlation : N/mm<sup>2</sup> = Kg/mm<sup>2</sup> × 9.8  
Kg/mm<sup>2</sup> = psi / 1422.3

SKCA-A-13

This Information is the best currently available on the subject. The results should, however, only be regarded as a general guide to material properties and not as a guarantee. Some of the properties can be changed as a result of supplier's efforts to improve the quality or production efficiency of the subject.

Note: Please read the Material Safety Data Sheet(MSDS) carefully prior to use.



## SH82 (500ga)

## Product Information

### ● Product Description

Skyrol® SH82 is an optically clear, glossy, two side chemically treated film. It provides an enhanced adhesion to various inks and adhesives. SH82 film is available in a range of thickness from 200ga to 750ga, and is used for high quality printing and solvent coating applications.

SH82 film is FDA approved for direct food contact in compliance with FDA 21 CFR 177.1630 (f).

### ● Typical Properties

Property	Unit	Value	Test Method
<b>General</b>			
Nominal Thickness	(Gauge) µm	<b>500</b> ( 125 )	SKC Method
<b>Mechanical</b>			
Tensile Strength	psi MD (Kg/mm <sup>2</sup> ) TD	25,000 (18) 29,000 (20)	ASTM D 882
Elongation At Break	% MD TD	195 140	ASTM D 882
<b>Surface</b>			
Coefficient of Friction	µk (Kinetic) µs (Static)	0.39 0.43	ASTM D1894
Surface Tension	Dyne Chemical	36	ASTM D 2578
<b>Optical</b>			
Haze	%	1.60	ASTM D 1003
Light Transmission	%	90.0	ASTM D 1003
Gloss	%	185	ASTM D 523
<b>Thermal</b>			
Heat Shrinkage	% MD TD	1.0 0.6	SKC Method ( 150°C×30 min )

Unit Correlation : N/mm<sup>2</sup> = Kg/mm<sup>2</sup> × 9.8  
Kg/mm<sup>2</sup> = psi / 1422.3

SKCA-A-13

This Information is the best currently available on the subject. The results should, however, only be regarded as a general guide to material properties and not as a guarantee. Some of the properties can be changed as a result of supplier's efforts to improve the quality or production efficiency of the subject.  
Note: Please read the Material Safety Data Sheet(MSDS) carefully prior to use.





## SH82 (600ga)

## Product Information

### ● Product Description

Skyrol® SH82 is an optically clear, glossy, two side chemically treated film. It provides an enhanced adhesion to various inks and adhesives. SH82 film is available in a range of thickness from 200ga to 750ga, and is used for high quality printing and solvent coating applications.

SH82 film is FDA approved for direct food contact in compliance with FDA 21 CFR 177.1630 (f).

### ● Typical Properties

Property	Unit	Value	Test Method
<b>General</b>			
Nominal Thickness	(Gauge) µm	<b>600</b> ( 150 )	SKC Method
<b>Mechanical</b>			
Tensile Strength	psi MD (Kg/mm <sup>2</sup> ) TD	24,000 (17) 28,000 (20)	ASTM D 882
Elongation At Break	% MD TD	215 145	ASTM D 882
<b>Surface</b>			
Coefficient of Friction	µk (Kinetic) µs (Static)	0.39 0.43	ASTM D1894
Surface Tension	Dyne Chemical	36	ASTM D 2578
<b>Optical</b>			
Haze	%	1.70	ASTM D 1003
Light Transmission	%	89.9	ASTM D 1003
Gloss	%	180	ASTM D 523
<b>Thermal</b>			
Heat Shrinkage	% MD TD	0.9 0.5	SKC Method ( 150°C×30 min )

Unit Correlation : N/mm<sup>2</sup> = Kg/mm<sup>2</sup> × 9.8  
Kg/mm<sup>2</sup> = psi / 1422.3

SKCA-A-13

This Information is the best currently available on the subject. The results should, however, only be regarded as a general guide to material properties and not as a guarantee. Some of the properties can be changed as a result of supplier's efforts to improve the quality or production efficiency of the subject.  
Note: Please read the Material Safety Data Sheet(MSDS) carefully prior to use.



# SH82 (650ga)

## Product Information

### ● Product Description

Skyrol® SH82 is an optically clear, glossy, two side chemically treated film. It provides an enhanced adhesion to various inks and adhesives. SH82 film is available in a range of thickness from 200ga to 750ga, and is used for high quality printing and solvent coating applications.

SH82 film is FDA approved for direct food contact in compliance with FDA 21 CFR 177.1630 (f).

### ● Typical Properties

Property	Unit	Value	Test Method
<b>General</b>			
Nominal Thickness	(Gauge) µm	<b>650</b> ( 165 )	SKC Method
<b>Mechanical</b>			
Tensile Strength	psi MD (Kg/mm <sup>2</sup> ) TD	23,000 (16) 27,000 (19)	ASTM D 882
Elongation At Break	% MD TD	235 150	ASTM D 882
<b>Surface</b>			
Coefficient of Friction	µk (Kinetic) µs (Static)	0.39 0.43	ASTM D1894
Surface Tension	Dyne Chemical	36	ASTM D 2578
<b>Optical</b>			
Haze	%	1.80	ASTM D 1003
Light Transmission	%	89.5	ASTM D 1003
Gloss	%	180	ASTM D 523
<b>Thermal</b>			
Heat Shrinkage	% MD TD	0.9 0.5	SKC Method ( 150°C×30 min )

Unit Correlation : N/mm<sup>2</sup> = Kg/mm<sup>2</sup> × 9.8  
Kg/mm<sup>2</sup> = psi / 1422.3

SKCA-A-13

This Information is the best currently available on the subject. The results should, however, only be regarded as a general guide to material properties and not as a guarantee. Some of the properties can be changed as a result of supplier's efforts to improve the quality or production efficiency of the subject.  
Note: Please read the Material Safety Data Sheet(MSDS) carefully prior to use.



## SH82 (700ga)

## Product Information

### ● Product Description

Skyrol® SH82 is an optically clear, glossy, two side chemically treated film. It provides an enhanced adhesion to various inks and adhesives. SH82 film is available in a range of thickness from 200ga to 750ga, and is used for high quality printing and solvent coating applications.

SH82 film is FDA approved for direct food contact in compliance with FDA 21 CFR 177.1630 (f).

### ● Typical Properties

Property	Unit	Value	Test Method
<b>General</b>			
Nominal Thickness	(Gauge) µm	<b>700</b> ( 175 )	SKC Method
<b>Mechanical</b>			
Tensile Strength	psi MD (Kg/mm <sup>2</sup> ) TD	22,000 (15) 26,000 (18)	ASTM D 882
Elongation At Break	% MD TD	250 150	ASTM D 882
<b>Surface</b>			
Coefficient of Friction	µk (Kinetic) µs (Static)	0.39 0.43	ASTM D1894
Surface Tension	Dyne Chemical	36	ASTM D 2578
<b>Optical</b>			
Haze	%	2.10	ASTM D 1003
Light Transmission	%	89.5	ASTM D 1003
Gloss	%	180	ASTM D 523
<b>Thermal</b>			
Heat Shrinkage	% MD TD	0.9 0.5	SKC Method ( 150°C×30 min )

Unit Correlation : N/mm<sup>2</sup> = Kg/mm<sup>2</sup> × 9.8  
Kg/mm<sup>2</sup> = psi / 1422.3

SKCA-A-13

This Information is the best currently available on the subject. The results should, however, only be regarded as a general guide to material properties and not as a guarantee. Some of the properties can be changed as a result of supplier's efforts to improve the quality or production efficiency of the subject.  
Note: Please read the Material Safety Data Sheet(MSDS) carefully prior to use.



## SH82 (750ga)

## Product Information

### ● Product Description

Skyrol® SH82 is an optically clear, glossy, two side chemically treated film. It provides an enhanced adhesion to various inks and adhesives. SH82 film is available in a range of thickness from 200ga to 750ga, and is used for high quality printing and solvent coating applications.

SH82 film is FDA approved for direct food contact in compliance with FDA 21 CFR 177.1630 (f).

### ● Typical Properties

Property	Unit	Value	Test Method
<b>General</b>			
Nominal Thickness	(Gauge) µm	<b>750</b> ( 188 )	SKC Method
<b>Mechanical</b>			
Tensile Strength	psi MD (Kg/mm <sup>2</sup> ) TD	21,000 (15) 25,500 (18)	ASTM D 882
Elongation At Break	% MD TD	255 150	ASTM D 882
<b>Surface</b>			
Coefficient of Friction	µk (Kinetic) µs (Static)	0.39 0.43	ASTM D1894
Surface Tension	Dyne Chemical	36	ASTM D 2578
<b>Optical</b>			
Haze	%	2.70	ASTM D 1003
Light Transmission	%	88.9	ASTM D 1003
Gloss	%	175	ASTM D 523
<b>Thermal</b>			
Heat Shrinkage	% MD TD	0.9 0.5	SKC Method ( 150°C×30 min )

Unit Correlation : N/mm<sup>2</sup> = Kg/mm<sup>2</sup> × 9.8  
Kg/mm<sup>2</sup> = psi / 1422.3

SKCA-A-13

This Information is the best currently available on the subject. The results should, however, only be regarded as a general guide to material properties and not as a guarantee. Some of the properties can be changed as a result of supplier's efforts to improve the quality or production efficiency of the subject.  
Note: Please read the Material Safety Data Sheet(MSDS) carefully prior to use.