

**DESCRIPTION:** Quick curing agent designed for impact and high strength flexibility. Easily mixed 1:1 ratio by volume. Low viscosity, no VOCs, 100% solids.

#### **SUGGESTED USES:**

Laminating, adhesives, fiberglass repairs and small castings.

#### PROPERTIES OF TAP GENERAL PURPOSE HARDENER:

Viscosity at 77°F, cps 1,400

Color (Gardener) 3 (New, color changes with age; Does not affect performance properties)

Weight Per Gallon 8.0 - 8.1lbs

Mix Ratio, Parts Per 100 Resin 85 by weight (1:1 volume)

Gel Time at  $70^{\circ}$ F (150 Grams) 10 - 15 minutes

Thin Film Set Time, Hours 3-4 Full Cure Time 7 days

## TYPICALLY CURED PROPERTIES W/ TAP GENERAL PURPOSE RESINS:

(Cure schedule: Gel at ambient + 2 hours at 100°C or 7 days at 77°F)

HDT (F) Heat Distortion Temp 115 ASTM D648-264

Shore D Hardness 79
Flexural Strength, psi 11,500
Flexural Modulus, ps Tensile Strength, psi 7,500
Tensile Modulus, psi Elongation % 5.0

#### **SAFETY PRECAUTIONS:**

# Health Considerations: Consult the TAP Plastics Material Safety Data Sheets.

This chemical system requires the use of proper safety equipment and procedures. Please follow the TAP Plastics product MSDS for detailed information and handling guidelines.

### For Your Protection:

The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions made concerning the products and their uses, applications, storage and handling are only the opinion of TAP Plastics. Users should conduct their own tests to determine the suitability of these products for their own particular purposes and of the storage and handling methods herein suggested. The toxicity and risk characteristics of products made by TAP Plastics will necessarily differ from the toxicity and risk characteristics developed when such products are used with other materials during a manufacturing process. The resulting risk characteristics should be determined and made known to ultimate end-users and processors. Because of numerous factors affecting results, TAP Plastics makes no warranty of any kind, express or implied, other than that the material conforms to its applicable current Standard Specifications. TAP Plastics hereby disclaims any and all other warranties, including but not limited to those of merchantability or fitness for a particular purpose. No statements made herein may be construed as a representation or warranty. The liability of TAP Plastics for any claims arising from or sounding in breach of warranty, negligence, strict liability, or otherwise shall be limited to the purchase price of the material.